

# **IMPACT PP B393G**

YUPLENE B393G is a propylene impact copolymer designed for injection molding application. YUPLENE B393G has high stiffness, excellent dimensional stability, good impact strength and has been listed by Underwriters Laboratories (UL). Its excellent flow property makes it suitable for various large size electrical appliances and thin wall products. YUPLENE B393G complies with FDA regulation 21 CFR177.1520

# **Application / Use Case**

Injection / Automobile applications, large container, Industrial parts for electronic

#### **Characteristics**

High Stiffness, Impact Strength, High folw

### **Specification**

|            | Value | Unit    | <b>Test Method</b> |
|------------|-------|---------|--------------------|
| Melt Index | 60.0  | g/10min | ASTM D1238         |

## **Physical Properties**

|                                      | Value | Unit               | Test Method |
|--------------------------------------|-------|--------------------|-------------|
| IZOD Impact Strength(Notched, 23°C)  | 7.0   | kg·cm/cm           | ASTM D256   |
| IZOD Impact Strength(Notched, -20°C) | 5.0   | kg·cm/cm           | ASTM D256   |
| Softening Point(Vicat)               | 150   | °C                 | ASTM D1525  |
| Tensile Strength at Yield            | 270   | kg/cm <sup>2</sup> | ASTM D638   |
| Elongation at Break                  | <500  | %                  | ASTM D638   |
| Flexural Modulus                     | 14000 | kg/cm <sup>2</sup> | ASTM D790   |

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea

Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea

Technology Tel. 82-42-866-7624 Fax. 82-42-866-7603

Online www.skglobalchemical.com

www.skchem.com

ISO 9001 Certified





001



| Hardness(Rockwell)                      | 90   | R Scale | ASTM D785  |
|---|------|---------|------------|
| Heat Distortion Temperature             | 110  | °C      | ASTM D648  |
| Accelerated Oven Aging(in Air at 150°C) | 360  | hr      | ASTM D3012 |
| Dupont Impact at -10°C                  | >20  | kg·cm   | ASTM D2794 |
| Spiral Flow                             | >800 | mm      | SK Method  |

These are typical properties only, and are not to be construed as specific limits.

Head Office

99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea

Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of Technology Online 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea Tel. 82-42-866-7624 Fax. 82-42-866-7603

www.skglobalchemical.com www.skchem.com ISO 9001 Certified



